

Technical Datasheet

MICROBEADS FOR PAVIMYC HB 2/C



Product Code: 07251 Flooring

DESCRIPTION

Polyethylene microbeads with average diameter of 250 microns, suitable for obtaining anti-slip properties on wet surfaces.

USE: INTERIOR-EXTERIOR

Used as an additive to obtain a class 3 slip rating (as per Pendulum test method according to standard UNE-ENV 12633:2003 Annex A) in PAVIMYC HB 2/C Floor systems.

PROPERTIES

- Easy to use
- Gives a homogeneous surface finish
- Does not alter the mechanical properties of the paint product
- Provides excellent surface hardness.
- Does not contain Volatile Organic Components.

CERTIFICATIONS

- Slip resistance rating: Class 3 as per UNE-ENV 12633, Annex A - Pavimyc HB 2/C

Finish: Textured

Colour: No colour alteration of paint

Density: $0,95 \pm 0,05$ gr/cc S/FR1002

Mix ratio in weight: 1 tub of microbeads for every 20 kg of paint.

07251

Format: aprox. 400 gr

Technical Datasheet

MICROBEADS FOR PAVIMYC HB 2/C



Product Code: 07251 Flooring

PREPARACIÓN DE SUPERFICIES

CONCRETE SURFACES. On newly laid concrete surfaces wait until concrete has fully set (min. 1 month). The surface must be completely dry. Pavement moisture should not exceed 4%, measured at a depth of 2 cm. It has to be firm and free from dust, laitance, grease and poorly adhered particles. Minimum tensile strength 15 kg/m². In order to achieve good adhesion on the concrete surface, it must be textured and free of grease stains, rubber, curing agents, lime milk and any foreign material.

Grease and rubber stains must be removed with solvent or detergents, rinsing after with water. Use shot blasting and milling if such stains do not disappear. The laitance and curing agents must be removed by milling or shot blasting, followed by vacuuming of the dust. This makes it possible to obtain a rough surface free of foreign materials. When there is any doubt about the quality of the floor preparation, we recommend making an application of paint on a representative sample area of the surface (1m²), to check the adhesion results before deciding to continue with the remainder of the job.

APPLICATION & USE

Mix microbeads into the paint before application in the following proportions:

1 tub of microbeads(400 gr) for every 20 kgs of paint.

Shake and mix until a homogeneous mixture is obtained.

Consult the application procedures of the paint product to be applied for full instructions.

SAFETY AND ENVIRONMENT

Minimize product waste by estimating the amount needed, taking into account the m², the porosity and texture of the substrate. Store excess material in a ventilated and dry place. The container must be clean and be the right size for the amount of leftover product. Close containers carefully and keep upright to avoid spillage. Preserve the containers from frost, high temperatures and direct exposure to the sun. Recover unused product for future use and save the environment.

Do not eat, drink or smoke during the preparation and application of the product.

Surface preparation and application operations must be carried out with the corresponding safety measures.

For more information consult the Safety Data Sheet.

In case of contact with eyes, wash with plenty of clean water. Keep out of the reach of children.

Do not discharge into drains or the environment.

Dispose of at an authorized waste collection point. Consult your city council about the correct recycling method of both the container and waste and leftover paint in accordance with the law and principles of environmental respect.

The information contained in this technical sheet may change and must be updated. Check www.juno.es or your nearest JUNO representative for the latest data sheet.

Application technical advice, whether verbal, written, or by testing, is based on JUNO's experience and technical knowledge. The data shown in this document should be considered a recommendation and as such does not imply any commitment, even with regard to possible third-party industrial property rights.

The application, use and transformation of the products supplied by JUNO are carried out by third parties. Consequently, the final result is the sole responsibility of the client, applicator or handler of the products and not of the supplying company. This document does not exempt the customer from carrying out his own examination of the products supplied, in order to verify its suitability for the procedures and purposes envisaged. In case of responsibility assumed by JUNO, it will be limited to the strict value of the merchandise supplied and used by the client, whatever the damages caused.

JUNO guarantees the quality of all its products, in accordance with the current General Conditions of Sale.

Industrias JUNO, S.A. - Barrio Sakoni, 10 - 48950 Erandio (Bizkaia) SPAIN - Tel.+34 944 670 062 - infoweb@juno.es - www.juno.es